

S-737 X H-14

Type : Neutral

S-737 X H-14

Conformances

AWS A5.17 / ASME SFA5.17 F7A(P)4-EH14
JIS Z3183 S502-H
EN ISO 14174 S A AB 1 / EN ISO 14171 S4
KR 3M,3YM

ABS 3M,3YM
LR 3M,3YM
DNV IIIYM
GL 3YM

Applications

- Storage tanks
- Pressure vessels
- Shipbuilding

Features

- Good performance and bead appearance
- Easy to remove slag
- Density : 1.1g/cm³

Current

AC, DC +

Basicity Index

1.6

Packages (Flux)

Tin Can 20kg(44lbs)
PE Bag 20kg(44lbs)

Flux Composition

Consumable	Chemical Composition, wt%			
	SiO ₂ + TiO ₂	CaO + MgO	Al ₂ O ₃ + MnO	CaF ₂

Diameter / Packaging

Diameter	Spool	Basket	Coil							Pac				
mm (in)	20kg (44lbs)	25kg (55lbs)	100kg (220lbs)	25kg (55lbs)	100kg (220lbs)	200kg (440lbs)	250kg (551lbs)	300kg (661lbs)	500kg (1102lbs)	200kg (440lbs)	250kg (551lbs)	300kg (661lbs)	350kg (771lbs)	400kg (881lbs)
1.6 (1/16)	✓			✓							✓			✓
2.0 (5/64)	✓			✓	✓	✓	✓					✓		
2.4 (3/32)	✓	✓		✓	✓	✓								
3.2 (1/8)		✓		✓	✓	✓	✓	✓			✓	✓	✓	
4.0 (5/32)		✓		✓	✓	✓		✓	✓	✓	✓	✓	✓	✓
4.8 (3/16)	✓			✓	✓			✓	✓					
6.4 (1/4)				✓	✓									



Typical Chemical Composition of All-Weld Metal(%)

Wire	C	Si	Mn	P	S	BM	Th.(mm)
H-14	0.08	0.31	1.60	0.025	0.019	SS400	25
	0.07	0.40	1.53	0.020	0.013	SM490	28

Typical Mechanical Properties of All-Weld Metal

Wire	YS Mpa(lbs/in ²)	TS Mpa(lbs/in ²)	EL (%)	Temp °C(°F)	CVN-Impact Value J (ft.-lbs)	BM	Th.(mm)
H-14	510 (74,000)	570 (82,800)	31	-40 (-40)	110 (81)	SS400	25
	-	540 (78,400)	-	-20 (-4)	60 (44)	SM490	28

Typical Welding Conditions

Wire	Dia. (mm)	Th. (mm)	Groove Design (mm)	Pass	Amp. (A)	Volt. (V)	Speed (cm/min)	Remarks
H-14	4.0	25		1~13	570	30	40	AW A5.17
H-14	3.2	28		1	450	28	35	1st Horizontal ML
				2~4	500	26	50	
				5 6~8	450 500	28 26	35 50	